



**ALLOY DATA SHEET**

ALLOY GROUP <sup>1</sup>	NUMERICAL DESIGNATION <sup>1</sup>	CHEMICAL DESIGNATION <sup>1</sup>	S.A.V. ALLOY CODE
<b>AISI5Cu</b>	<b>EN AB - 45500</b>	<b>EN AB-AI Si7Cu0,5Mg</b>	<b>01012568</b>

<sup>1</sup>EN 1676:2020 Aluminium and aluminium alloys – Alloyed ingots for remelting – Specifications

**INGOTS CHEMICAL COMPOSITION**

Alloy	% wt	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Other Each	Other Total
EN AB - 45500 <sup>1</sup>	Min.	6,5	-	0,2	-	0,25	-	-	-	-	-	-	-	-
	Max	7,5	0,25	0,7	0,15	0,45	-	-	0,07	-	-	0,20	0,03	0,10

<sup>1</sup>EN 1676:2020 Aluminium and aluminium alloys – Alloyed ingots for remelting – Specifications

**CASTINGS CHEMICAL COMPOSITION**

Alloy	% wt	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Other Each	Other Total
EN AC - 45500 <sup>2</sup>	Min.	6,5	-	0,2	-	0,20	-	-	-	-	-	-	-	-
	Max	7,5	0,25	0,7	0,15	0,45	-	-	0,07	-	-	0,20	0,03	0,10

<sup>2</sup>EN 1706:2020 Aluminium and aluminium alloys – Castings – Chemical composition and mechanical properties

**MECHANICAL PROPERTIES<sup>2</sup>**

Minimum mechanical properties for separately cast sample

Casting method	Temper designation	Tensile strength $R_m$ [MPa] min.	Yield strength $R_{p0,2}$ [MPa] min	Elongation A [%] min	Brinnell hardness HBW min
Sand Casting	T6	250	190	1	85
Chill Casting	T6	320	240	4	100
Low Pressure die Casting	T6	320	240	4	100
Investment Casting	-	-	-	-	-
Pressure die Casting	-	-	-	-	-
Potential mechanical properties of test specimens from castings <sup>3</sup>	-4	310	260	5	100

<sup>2</sup>EN 1706:2020 Aluminium and aluminium alloys – Castings – Chemical composition and mechanical properties

<sup>3</sup>It cannot be assumed that the given values can be reached throughout the casting since mechanical properties strongly depend on the solidification rate, the heat treatment and the soundness of the casting. Therefore, the values and the position of the area where those values can be achieved shall be agreed between supplier and customer.

<sup>4</sup> The heat treatment has to be defined according to the type of casting produced.

**PHYSICAL PROPERTIES<sup>2</sup>**

CASTING METHOD	SAND CASTING		OTHER PROPERTIES	MACHINABILITY IN THE AS CAST STATE	
	PERMANENT MOULD CASTING	✓		MACHINABILITY AFTER HEAT TREATMENT	B
PRESSURE DIE CASTING	-	RESISTANCE TO CORROSION	B/C		
INVESTMENT CASTING	-	DECORATIVE ANODIZING	D		
CASTABILITY	FLUIDITY	B	ABILITY TO BE WELDED	B	
	RESISTANCE TO HOT TEARING	B	ABILITY TO BE POLISHED	C	
	PRESSURE TIGHTNESS	B	LINEAR THERMAL EXPANSION [10 <sup>-6</sup> /K] (293 K-373 K)	22,00	
MECHANICAL PROPERTIES	STRENGTH AT ROOM TEMPERATURE	A	ELECTRICAL CONDUCTIVITY [MS/m]	16 - 22	
	STRENGTH AT HIGH TEMPERATURE 200 °C	B	THERMAL CONDUCTIVITY [W/(m K)]	150 - 165	
	DUCTILITY (SHOCK RESISTANCE)	A/B			
	FATIGUE RESISTANCE [MPa]	80 - 110			

✓ Indicates the most commonly casting process used for each alloys  
 A: Optimal    B: good    C: Fair    D: Poor    E: Not Recommended    F: Unsuitable

<sup>2</sup>EN 1706:2020 Aluminium and aluminium alloys – Castings – Chemical composition and mechanical properties



**HEAT TREATMENT DESIGNATION<sup>2</sup>**

ABBREVIATION	HEAT TREATMENT
F	AS CAST
O	ANNEALED
T1	CONTROLLED COOLING FROM CASTING AND NATURALLY AGED
T4	SOLUTION HEAT TREATED AND NATURALLY AGED WHERE APPLICABLE
T5	CONTROLLED COOLING FROM CASTING AND ARTIFICIALLY AGED OR OVER-AGED
T6	SOLUTION HEAT TREATED AND ARTIFICIALLY AGED
T64	SOLUTION HEAT TREATED AND ARTIFICIALLY UNDER-AGED
T7	SOLUTION HEAT TREATED AND ARTIFICIALLY OVER-AGED (STABILIZED)

<sup>2</sup>EN 1706:2020 Aluminium and aluminium alloys – Castings – Chemical composition and mechanical properties

**CORRELATION WITH OTHER STANDARDS**

EN AB - 45500 / EN AC - 45500

NATION	U.S.A.	JAPAN	INTERNATIONAL	ITALY	FRANCE	GERMANY	GREAT BRITAIN
STANDARD	B179	H2211	17615	UNI	NF A57-702	1725	BS 1490
STATUS	ACTIVE	ACTIVE	ACTIVE	SUPERSEDED	SUPERSEDED	SUPERSEDED	SUPERSEDED
IDENTICAL STANDARD	INGOT SPECIFICATION	-	-	-	-	-	-
SIMILAR STANDARD	INGOT SPECIFICATION	-	-	-	-	-	-

Any dissemination, copy or reproduction of this document, even if only for extract, is prohibited.

The physical and mechanical properties shown in this data sheet have a mere informative purpose since they are detected on sample cast separately in specific cooling conditions. No liability is accepted for decisions based on the indicated physical and mechanical properties and no guarantee is given for the physical and mechanical properties indicated, as they depend on the specific conditions of casting of the cast pieces.